Paraffinic Wax	Congealing Point °C	Cone penetrating mm/10 @ 25°C	Oil Content %
Fully Refined			
Wax 55-P	52,0 - 54,0	53 - 56	3,0
Wax 56-P	56,0 - 58,0	18	0,4
Wax 58-P	57,0 - 60,0	18	0,4
Wax 64-P	64,0 - 66,0	19	0,5
Wax 80-P	68,0 - 72,0	80	4,5
Wax 2311-P	62,0 - 64,0	15 - 18	0,7 - 0,9
Many other grades are available on request			
Hywax			
Hywax 5105 **	52.0 - 54.0	21 - 28	0.0 - 1.5
Hywax 5603	56.0 - 58.0	15 - 19	0.0 - 0.5
Hywax 6403	62.0 - 63.0	16 - 22	0.0 - 0.5
Hywax 8021	44.0 - 48.0	60 - 100	0.5 - 3.0
Hywax 0587 - Histology Wax	54,0 - 56,0	14 - 18	0.0 - 0.5
** Fullfils all Ph.Eur and BfR requirements			
Many other Hywax grades are available on request			

Slack Wax	Congealing Point °C	Cone penetrating mm/10 @ 25°C	Oil Content %
Wax 50-TW	50,0 - 70,0	45 - 68	6.0 - 10.0
Wax 60-TW	60,0 - 62,0	55 - 65	8 - 10
Wax 68-TW	66,0 - 69,0	96-105	13
Wax 5669-P	66.0 - 71.0	90 - 140	6.0 - 10.0
Many other grades are available on request			
* colour measured as per DIN ISO 2029			

Microcrystalline	Congealing Point °C	Cone penetrating mm/10 @ 25°C	Oil Content %
Microcrystalline			
Wax 15-MW	77,0 - 81,0	14 - 18	0,0 - 1,0
Wax 30-MW	72,0 - 75,0	27 - 30	0,0 - 2,0
Wax 80-MW	64,0 - 72,0	80	4,5
Wax 7030-MW	66,0 - 72,0	30 - 40	1,5
Wax 7060-MW	72,0 - 76,0	55 - 62	3,9
Wax 8020-MW	74,0 - 76,0	21	1,2
Purity			
FDA 172.886			
Many other grades are available on request			
Hywax			
Hywax 1800	70.0 - 80.0	18 - 22	0.0 - 2.0
Hywax 2528	70 - 75	25 - 35	0.0 - 4.0
Hywax 3971	70 - 75	25 - 33	0.0- 2.0
Many other Hywax grades are available on request			

Synthetic Wax	Congealing Point °C	Cone penetrating mm/10 @ 25°C	Oil Content %
Fisher-Tropsch			
Wax FT-70 *	>70	10 - 16	<4
Wax FT-80 *	76,0 - 82,0	<10	<3,5
Wax FT-100 *	>100	1 max	<1,0
* non FDA			
Hywax			
Hywax 2720	98 - 105	0 - 1	<0,2
Hywax 2781	76 - 82	4 - 15	<0,5
Hymicro 20 - G*	98 - 105	0 - 1	<0,2
* non FDA			
Hycos 303	60 - 67	12 - 25	<0,2
Hycos 75	75 - 82	5 - 15	<0,2
Hycos 80	80 - 85	4 - 9	<0,2
Other Hycos grades are available on request			
Sasolwax			
Sasolwax H1	96 - 100	1 max	<0,2
Sasolwax C-80	80 - 85	4 - 9	0,5
Sasolwax C105	102 - 108	1 max	<0,2
Sasolwax Spray 30-G	96.0 - 100.0	0.0 - 1.0	<0,2
Purity			
FDA 172.615			
FDA 175.105			
FDA 175.250			
FDA 175.300			
BfR XXV			
Other Sasolwax grades are available on request			

Wax Emulsion	Emulsifier Type	Viscosity, Brookfield, 25°C	pH	Solid Content %
Wax Emulsion 50-MW	Anionic	200 rpm Max.	8,0 - 10,0	44 - 48
Wax Emulsion 45-P (FDA ap.)	Anionic	290 - 310 mPa*s	8,0 - 9,0	43 - 48
Wax Emulsion 150-P	Anionic	1300 rpm Max.	8,5 - 10,5	44 - 50
Wax Emulsion FF-40 *	Anionic	160 - 180 mPa*s	8,0 - 10,0	37 - 42
Wax Emulsion FF-60	Anionic	160 - 180 mPa*s	8,0 - 10,0	57 - 62
* Bio-Based				
Many other emulsion grades are available on request				
Hywax				
Hywax Hydrowax-M	Anionic	250 mPa*s	8,5	44-48
Hywax Hydrowax-Q	Anionic	850 mPa*s	6,5	48 - 52
Hywax Hydrowax-46	Cationic	200 mPa*s	7	58 - 62
Hywax Hydrowax-115**	Anionic	300 mPa*s	8,0 - 9,5	44 - 48
** Fullfils all FDA and BfR requirements				
Many other Hywax grades are available on request				